

## Metalvac E

### Description:

Metallized label paper designed for non-returnable containers such as bottles, cans and jars

### End uses:

Labels for 1-way bottles, Wraparound labels, Wine and spirit labels

### Print methods:

Conventional offset, Flexo solvent-based, Rotogravure solvent-based

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Leitza mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Leitza](#)
- [Paper Profile Metalvac](#)

For applications that require specific certifications or approvals, please contact our sales teams.

## Metalvac E

### Technical specifications

Property	Test Method	Unit	Tolerance	73	78	83	93
Substance	ISO 536	g/m <sup>2</sup>	± 4 %	73	78	83	93
Thickness	ISO 534	µm	± 5	63	67	70	80
Gloss (silver, plain)	ISO 7668	%	± 20 %	425	425	425	425
Cobb (uncoated side)	ISO 535	g/m <sup>2</sup>	± 4	18.0	18.0	18.0	18.0
Absolute humidity	ISO 287	%	± 1	5.0	5.0	5.0	5.0
Relative humidity	TAPPI T502	%	± 7	47.0	47.0	47.0	47.0
Dry tensile strength MD	ISO 1924-2	kg/15mm	-1.0	6.0	6.0	7.0	7.5
Dry tensile strength CD	ISO 1924-2	kg/15mm	-0.5	4.3	4.3	5.0	5.5

**Storage Recommendations:** The material must be stored at a temperature of 15-25 °C and 50-60% relative humidity. In case of sheets in pallets, do not store pallets more than two heights. Keep the paper in its original wrapping when it is not being used. Condition the paper to temperature of print shop at least 24 hours before use.

Values are subject to change without notice.

Last update: 04/15/2026