

Metalvac FP OH Proof

Description:

Metallized paper designed to deliver high visual impact while maintaining stable surface performance under alcohol exposure, suitable for use as a lamination layer.

End uses:

Flexible packaging, Food contact, Alcohol resistant packaging (perfumes, cosmetics, etc.), Liqueur-filled chocolate packaging (pouches, sachets, etc.), Wrapping solutions, Lamination

Print methods:

Conventional offset, Flexo solvent-based, Rotogravure solvent-based

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Leitza mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Leitza](#)
- [Paper Profile Metalvac](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Metalvac FP OH Proof

Technical specifications

Property	Test Method	Unit	Tolerance	53
Substance	ISO 536	g/m ²	±4%	53
Thickness	ISO 534	µm	±5	48
Gloss (silver, plain)	ISO 7668	% _o	±20%	420
Cobb (uncoated side)	ISO 535	g/m ²	±4	22
Absolute humidity	ISO 287	%	±1	4.5
Relative humidity	TAPPI T502	%	±7	40
Dry tensile strength MD	ISO 1924-2	kg/15mm	-1	4.8
Dry tensile strength CD	ISO 1924-2	kg/15mm	-0.5	2.7

Values are subject to change without notice.

Last update: 04/15/2026