

## Metalvac GP

### Description:

Functional metallized paper with high resistance to grease and water vapour. No PFAs Added.

Suitable for butter wrapping and other fatty food packaging.

Good deadfolding properties.

Printable on the metallized face.

### End uses:

Flexible packaging, Food contact

### Print methods:

Offset, Rotogravure, Flexo

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Leitza mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Leitza](#)
- [Paper Profile Metalvac](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## Metalvac GP

### Technical specifications

Property	Test Method	Unit	Tolerance	75
Substance	ISO 536	g/m <sup>2</sup>	±4 %	75
Thickness	ISO 534	µm	± 5	60
Gloss	ISO 7668	%o	± 20%	350
Tensile strength MD	ISO 1924-2	kg/15mm	- 1	6.0
Tensile strength CD	ISO 1924-2	kg/15mm	- 0.5	3.6
Resistance to palm oil	ASTM-F119	h	≥ 24	≥ 24
Cobb (uncoated side)	ISO 535	g/m <sup>2</sup>	≤ 6	3
WVTR (23°C, 85% HR)	ASTM E96	g/m <sup>2</sup> (24h)	≤ 15	11

**Storage recommendations:** Ideally, paper should be stored at 50% (±5%) relative humidity and 23 °C (±2) and covered with original packaging. Avoid extreme temperature and humidity.

**Recommendations of use:** Best Before 12 months after dispatch from our factory.

Customers are responsible of their own product testing, evaluation and safety procedures.

Values are subject to change without notice.

Last update: 04/15/2026