

Creaset A GP

Description:

One-side coated paper for grease proof self-adhesive labels. No PFAS added.

For Inkjet UV and Flexo UV inks, we recommend applying a primer beforehand.

End uses:

Self-adhesive label facestock, Greaseproof labels

Print methods:

Conventional offset, UV offset, Flexo solvent-based, Flexo water-based, Flexo UV, Rotogravure solvent-based, Rotogravure water-based, Inkjet UV, Inkjet water-based

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Motril mill](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creaset - Motril](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Motril](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset A GP

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90
Substance	ISO 536 TAPPI T410	g/m ²	±4%	70	80	90
Thickness	ISO 534 TAPPI T411	µm	±4%	58	66	76
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	68	68	68
Parker roughness	ISO 8791-4 TAPPI T555	µm	<1.4	1.1	1.1	1.1
Cobb (uncoated side)	ISO 535 TAPPI T411	g/m ²	±5	24	24	24
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-0.4	4.5	5.1	5.7
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.3	2.6	3.0	3.2
Kit (coated side)	TAPPI UM 559	index	-1	9	9	9
Kit (uncoated side)	TAPPI UM 559	index	-1	9	9	9

Values are subject to change without notice.

Last update: 04/15/2026