

Creaset A

Description:

One-side coated paper for self-adhesive labels.

End uses:

Self-adhesive label facestock

Print methods:

Conventional offset, UV offset, Flexo solvent-based, Flexo water-based, Flexo UV, Rotogravure solvent-based, Rotogravure water-based, Inkjet UV, Inkjet water-based

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Motril mill](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creaset - Motril](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Motril](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset A

Technical specifications

Property	Test Method	Unit	Tolerance	78	80	90	100	120
Substance	ISO 536 TAPPI T410	g/m ²	±2% (78) ±4% (≥80)	78	80	90	100	120
Thickness	ISO 534 TAPPI T411	µm	±4%	67	69	78	90	109
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	66	66	66	67	68
Parker roughness	ISO 8791-4 TAPPI T555	µm	<1.4	1.1	1.1	1.1	1.1	1.2
Cobb (uncoated side)	ISO 535 TAPPI T441	g/m ²	±5	30	30	30	30	30
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-0.3	4.7	4.8	5.1	5.4	6.5
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.3	2.9	3	3.2	3.4	4.1

Values are subject to change without notice.

Last update: 04/15/2026