

Creaset GP FP

Description:

One-side coated grease proof gloss paper for Flexible Packaging. Without added PFAS.

For lamination, we recommend using synthetic glues.

For UV inks, we recommend applying a primer beforehand.

End uses:

Flexible packaging

Print methods:

Flexo, Offset, Rotogravure

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Motril mill](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creaset - Motril](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Motril](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset GP FP

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100
Substance	ISO 536 TAPPI T410	g/m ²	±4%	70	80	90	100
Thickness	ISO 534 TAPPI T411	µm	±4%	58	66	76	86
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	68	68	68	68
Brightness R457/D65	ISO 2470-2	%	±2	81	81	81	81
Parker roughness	ISO 8791-4 TAPPI T555	µm	<1.4	1.1	1.1	1.1	1.1
Cobb (uncoated side)	ISO 535 TAPPI T411	g/m ²	±5	24	24	24	24
Absolute humidity	ISO 638 TAPPI T412	%	±0.5	4.7	4.7	4.7	4.7
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-0.4	4.5	5.1	5.7	6.1
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.3	2.6	3	3.2	3.5
Kit (coated side)	TAPPI UM 559	index	-1	9	9	9	9
Kit (uncoated side)	TAPPI UM 559	index	-1	9	9	9	9

Values are subject to change without notice.

Last update: 04/15/2026