

## Creaset GP

### Description:

One-side coated grease proof gloss paper for standard or wraparound labels. Designed for labels used on plastic and glass containers such as olive oil and other greasy food products. The paper is produced without added PFAS

For Flexo UV and Inkjet UV inks, we recommend applying a primer beforehand

### End uses:

Labels for 1-way bottles, Wraparound labels

### Print methods:

Conventional offset, UV offset, Flexo solvent-based, Flexo water-based, Flexo UV, Rotogravure solvent-based, Rotogravure water-based, Inkjet UV, Inkjet water-based

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Motril mill](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creaset - Motril](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)
- [FSSC 22000 Food Safety - Motril](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## Creaset GP

### Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90
Substance	ISO 536 TAPPI T410	g/m <sup>2</sup>	±4%	70	80	90
Thickness	ISO 534 TAPPI T411	µm	±4%	58	66	76
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	68	68	68
Parker roughness	ISO 8791-4 TAPPI T555	µm	<1.4	1.1	1.1	1.1
Cobb (uncoated side)	ISO 535 TAPPI T411	g/m <sup>2</sup>	±5	24	24	24
Absolute humidity	ISO 638 TAPPI T412	%	±0.5	4.7	4.7	4.7
Relative humidity	TAPPI T502	%	±7	50	50	50
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-0.4	4.5	5.1	5.7
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.3	2.6	3.0	3.2
Kit (coated side)	TAPPI UM 559	index	-1	9	9	9
Kit (uncoated side)	TAPPI UM 559	index	-1	9	9	9

Values are subject to change without notice.

Last update: 04/15/2026