

Creaset HGP

Description:

One side coated paper with high grease proof barrier, without added PFAS.
For UV inks, we recommend applying a primer beforehand.

End uses:

Flexible packaging

Print methods:

Flexo, Offset

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset HGP

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90
Substance	ISO 536 TAPPI T410	g/m ²	±4%	70	80	90
Thickness	ISO 534 TAPPI T411	µm	±5	57	65	72
Brightness R457/D65	ISO 2470-2	%	±2	81	81	81
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-0.4	4.3	4.9	5.5
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.3	2.5	2.9	3.1
Cobb (functional side)	ISO 535	g/m ²	<10	6	6	6
Resistance to palm oil	ISO 16532-1	h	-	8	8	8
Kit (functional side)	TAPPI UM 559	index	-	10	10	10

Storage recommendations: Ideally, paper should be stored at 50% (±5%) relative humidity and 23 °C (±2) and covered with original packaging. Avoid extreme temperatures and humidity. Do not stack.

Recommendations of use: Best Before 12 months after dispatch from our factory.

Customers are responsible of their own product testing, evaluation and safety procedures.

Values are subject to change without notice.

Last update: 04/15/2026