# Creaset A GP

## Description:

One-side coated paper for grease proof self-adhesive labels. No PFAS added.

For Inkjet UV and Flexo UV inks, we recommend applying a primer beforehand.

## End uses:

Self-adhesive label facestock, Greaseproof labels

## Print methods:

Conventional offset, UV offset, Flexo solvent-based, Flexo water-based, Flexo UV, Rotogravure solvent-based, Rotogravure water-based, Inkjet UV, Inkjet water-based

## Certificates:

- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001  Environment
- EMAS Motril mill
- ISO 50001 Energy Efficiency
- Paper Profile Creaset - Motril
- ISO 9001 Quality
- ISO 45001  Health and Safety - Lecta
- FSSC 22000 Food Safety - Motril

For further details regarding compliance with food contact regulation, please contact our sales teams.

# Creaset A GP

## Technical specifications

| Property | Test Method | Unit | Tolerance | 70 | 80 | 90 |
|---|---|---|---|---|---|---|
| Substance | ISO 536<br>TAPPI T410 | g/m² | ±4% | 70 | 80 | 90 |
| Thickness | ISO 534<br>TAPPI T411 | µm | ±4% | 58 | 66 | 76 |
| Paper gloss | ISO 8254-1<br>TAPPI T480 | % | ±5 | 68 | 68 | 68 |
| Parker roughness | ISO 8791-4<br>TAPPI T555 | µm | <1.4 | 1.1 | 1.1 | 1.1 |
| Cobb (uncoated side) | ISO 535<br>TAPPI T411 | g/m² | ±5 | 24 | 24 | 24 |
| Tensile strength MD | ISO 1924-2<br>TAPPI T494 | kN/m | -0.4 | 4.5 | 5.1 | 5.7 |
| Tensile strength CD | ISO 1924-2<br>TAPPI T494 | kN/m | -0.3 | 2.6 | 3.0 | 3.2 |
| Kit (coated side) | TAPPI UM 559 | index | -1 | 9 | 9 | 9 |
| Kit (uncoated side) | TAPPI UM 559 | index | -1 | 9 | 9 | 9 |

Values are subject to change without notice.

Last update: 07/22/2026