Creaset FP White

Description:

One-side coated gloss paper for flexible packaging applications

End uses:

Flexible packaging

Print methods:

Flexo, Offset, Rotogravure

Certificates:

- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001 Environment
- EMAS Motril mill
- ISO 50001 Energy Efficiency
- Paper Profile Creaset - Motril
- ISO 9001 Quality
- ISO 45001 Health and Safety - Lecta
- FSSC 22000 Food Safety - Motril

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset FP White

Technical specifications

Property	Test Method	Unit	Tolerance	60	70	80	90
Substance	ISO 536 TAPPI T410	g/m²	±4%	60	70	80	90
Thickness	ISO 534 TAPPI T411	µm	±4%	52	58	65.5	74
Parker roughness	ISO 8791-4 TAPPI T555	µm	≤1.0 (60) +0.2 (70, 80, 90)	0.8	1.0	0.9	0.9
Cobb (uncoated side)	ISO 535 TAPPI T411	g/m²	±4	23	24	24	24
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	71	72	72	72
Taber stiffness MD	ISO 2493 TAPPI T489	gf*cm	-25%	0.35	0.6	0.85	1.2
Opacity	ISO 2471 TAPPI T519	%	-2	80	85	87	88.5

Values are subject to change without notice.

Last update: 07/22/2026