Creaset RG

Description:

One-side coated gloss paper for hot melt wraparounds such as yoghurt banderoles. For rotogravure printing.

End uses:

Wraparound labels, Flexible packaging

Print methods:

Rotogravure

Certificates:

- Creaset Range List of certificates
- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001 Environment
- EMAS Motril mill
- ISO 50001 Energy Efficiency
- Paper Profile Creaset - Motril
- ISO 9001 Quality
- ISO 45001 Health and Safety - Lecta
- FSSC 22000 Food Safety - Motril

For further details regarding compliance with food contact regulation, please contact our sales teams.

Creaset RG

Technical specifications

Property	Test Method	Unit	Tolerance	90	95	110
Substance	ISO 536 TAPPI T410	g/m²	±4%	90	95	110
Taber stiffness CD	ISO 2493	gf*cm	-10%	0.75	0.9	1.2
Taber stiffness MD	ISO 2493	gf*cm	-10%	1.6	1.9	2.4
Tensile strength CD	ISO 1924-2	kN/m	-0.4	2.9	-	3.5
Tensile strength MD	ISO 1924-2	kN/m	-0.7	5.3	5.5	6
Thickness	ISO 534 TAPPI T411	µm	±4%	79	84	98
Bekk smoothness (coated side)	ISO 5627 TAPPI T475	sec.	≥0,8*STD	1000	900	600
Cobb (uncoated side)	ISO 535 TAPPI T441	g/m²	±5	25	25	25
Paper gloss	ISO 8254 TAPPI T480	%	±5	75	75	75

Values are subject to change without notice.

Last update: 07/22/2026