Termax TC20X 72

Description

Top-coated thermal paper with excellent resistance to scratching, grease, solvents, water and plasticizers.

Phenol free.

Image durability: 15 years at correct handling and storage conditions for thermal paper.

End uses

Label facestock, Food labelling, Lottery and gaming tickets, Transport tickets

Print methods

Flexo, Offset

Certificates

- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001 Environment
- EMAS Leitza mill
- ISO 50001 Energy Efficiency
- ISO 9001 Quality
- ISO 45001 Health and Safety - Lecta
- Paper Profile Termax

For further details regarding compliance with food contact regulation, please contact our sales teams.

Termax TC20X 72

Physical Properties

Property	Test Method	Unit	Value	Tolerance
Substance	ISO 536	g/m² lbs (17x22-500 sheets)	72 19.1	± 4%
Thickness	ISO 534	µm mils	76 2.99	± 3
Bekk smoothness	ISO 5627	s	1500	≥ 1000
Brightness	ISO 2470	%	92	≥ 90
Tensile strength CD	ISO 1924-2	kN/m	2.1	- 0.5
Tensile strength MD	ISO 1924-2	kN/m	4.5	- 1.0

Stability Properties

Property	Conditions	Image Stability	Paper Stability
Heat resistance	60°C, 30% HR, 24h	≥ 90%	≤ 0.12 D.O.
Humidity resistance	40°C, 90% HR, 24h	≥ 90%	≤ 0.12 D.O.
Light resistance	5.000 Lux, 100h	≥ 90%	≤ 0.10 D.O.

Image Sensitivity

Dynamic Sensitivity



Static Sensitivity



Values are subject to change without notice.
Last update: 07/22/2026