Termax TC30X 135

Description

Top-coated thermal paper of high grammage, with excellent resistance to scratching, grease, solvents, water and plasticizers.

Phenol free.

Image durability: 15 years at correct handling and storage conditions for thermal paper.

End uses

Transport tickets, Boarding passes, Entertainment tickets, Tags, Retail labels, bags and packaging, Shipping and logistics labels

Print methods

Flexo, Offset

Certificates

- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001 Environment
- EMAS Leitza mill
- ISO 50001 Energy Efficiency
- ISO 9001 Quality
- ISO 45001 Health and Safety - Lecta
- Paper Profile Termax

For further details regarding compliance with food contact regulation, please contact our sales teams.

Termax TC30X 135

Physical Properties

Property	Test Method	Unit	Value	Tolerance
Substance	ISO 536	g/m² lbs (17x22-500 sheets)	135 35.9	± 4%
Thickness	ISO 534	µm mils	149 5.87	± 5
Bekk smoothness	ISO 5627	s	800	≥ 500
Brightness	ISO 2470	%	95	≥ 90
Tensile strength CD	ISO 1924-2	kN/m	3.5	- 0.5
Tensile strength MD	ISO 1924-2	kN/m	6.5	- 1.0

Stability Properties

Property	Conditions	Image Stability	Paper Stability
Heat resistance	60°C, 30% HR, 24h	≥ 90%	≤ 0.12 D.O.
Humidity resistance	40°C, 90% HR, 24h	≥ 90%	≤ 0.12 D.O.
Light resistance	5.000 Lux, 100h	≥ 90%	≤ 0.10 D.O.

Image Sensitivity





Values are subject to change without notice.
Last update: 07/22/2026