Termax TEX 48

Description

Standard thermal paper for POS applications, with standard sensitivity and good printability for high speed thermal printers.

Phenol free.

Image durability: 10 years at correct handling and storage conditions for thermal paper.

End uses

POS receipts, ATM receipts, Bank statements, Coupons, Faxes, Kiosks, Medical charts

Print methods

Flexo, Offset

Certificates

- Lecta Information BPS REACH
- PEFC Chain of Custody (multisite)
- FSC Chain of Custody (multisite)
- ISO 14001 Environment
- EMAS Leitza mill
- ISO 50001 Energy Efficiency
- ISO 9001 Quality
- ISO 45001 Health and Safety - Lecta
- Paper Profile Termax

For further details regarding compliance with food contact regulation, please contact our sales teams.

Termax TEX 48

Physical Properties

Property	Test Method	Unit	Value	Tolerance
Substance	ISO 536	g/m² lbs (17x22-500 sheets)	48 12.8	± 4%
Thickness	ISO 534	µm mils	52 2.09	± 5 ± 0.2
Bekk smoothness	ISO 5627	s	300	≥ 200
Brightness	ISO 2470	%	90	≥ 85
Tensile strength CD	ISO 1924-2	kN/m	1.0	-0.5
Tensile strength MD	ISO 1924-2	kN/m	2.5	-1.0

Stability Properties

Property	Conditions	Image Stability	Paper Stability
Heat resistance	60°C, 30% HR, 24h	≥ 70%	≤ 0.15 D.O.
Humidity resistance	40°C, 90% HR, 24h	≥ 70%	≤ 0.15 D.O.
Light resistance	5.000 Lux, 100h	≥ 90%	≤ 0.12 D.O.

Image Sensitivity





Values are subject to change without notice.
Last update: 07/22/2026