

Coral Book Digital Ivory 1.2

Description:

Uncoated paper with a 1.2 bulk for digital printing and an off-white shade, aimed at the publishing sector. It is an offset paper made with chemical pulp, designed to offer excellent performance on press.

It is guaranteed for laser digital printing and laser pre-print, and it is recommended by the main digital printing brands.

Wide range of grammages and formats, available in sheets..

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Postcards

Print methods:

Digital, Laser/Dry toner

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Coral Book - Sant Joan les Fonts](#)
- [Paper Profile Coral Book - Zaragoza](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral Book Digital Ivory 1.2

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100
Substance	ISO 536 TAPPI T410	g/m ²	±4%	70	80	90	100
Thickness	ISO 534 TAPPI T411	µm	-	84	96	108	119
Bulk	ISO 534 TAPPI T411	cm ³ /g	±0.03	1.2	1.2	1.2	1.2
Opacity	ISO 2471 TAPPI T519	%	-2.0	88.0	90.0	92.0	93.0
Color a* D65/10°	ISO 5631-2	abs.	-	-0.05	-0.05	-0.05	-0.05
Color b* D65/10°	ISO 5631-2	abs.	-	12.3	12.3	12.3	12.3
Bendtsen roughness	ISO 8791-2 TAPPI T555	ml/min	±50	150	150	150	160
Cobb	ISO 535 TAPPI T441	g/m ²	±5	30	30	30	35
Relative humidity	TAPPI T502	%	±7	38	38	38	38

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature. In any case, extremes of temperature and humidity must be avoided.

The product's technical properties are guaranteed 12 months after production.

Values are subject to change without notice.

Last update: 04/15/2026