

Coral Book Digital White

Description:

Uncoated white paper with a 1.2 bulk, specially recommended for digital printing, HP Indigo certified.

It is guaranteed for laser digital printing and laser pre-print and is recommended by the main digital printing brands.

Available in a wide range of substances and formats, in sheets.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Digital, Laser/Dry toner

Certificates:

- [HP Indigo - Coral Book Digital White 70g](#)
- [HP Indigo - Coral Book Digital White 80g](#)
- [HP Indigo - Coral Book Digital White 90g](#)
- [HP Indigo - Coral Book Digital White 100g](#)
- [HP Indigo - Coral Book Digital White 120g](#)
- [HP Indigo - Coral Book Digital White 140g](#)
- [HP Indigo - Coral Book Digital White 170g](#)
- [HP Indigo - Coral Book Digital White 190g](#)
- [HP Indigo - Coral Book Digital White 250g](#)
- [HP Indigo - Coral Book Digital White 300g](#)
- [HP Indigo - Coral Book Digital White 350g](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Coral Book - Sant Joan les Fonts](#)
- [Paper Profile Coral Book - Zaragoza](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral Book Digital White

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100	120	140	160	190	250	300	350
Substance	ISO 536	g/m ²	±4%	70	80	90	100	120	140	160	190	250	300	350
Thickness	ISO 534 TAPPI T411	µm	±4%	84	96	108	119	142	164	185	218	287	345	402
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1.20	1.20	1.20	1.19	1.18	1.17	1.16	1.15	1.15	1.15	1.15
Opacity	ISO 2471:1977 TAPPI T519	%	-2	91.0	93.0	95.0	96.0	98.0	99	-	-	-	-	-
Brightness R457/D65	ISO 2470-2 TAPPI T452	%	±2	103	103	103	103	103	103	103	103	103	103	103
Whiteness D65/10°	ISO 11475 TAPPI T562	CIE	±5	148	148	148	148	148	148	148	148	148	148	148
Bendtsen roughness	ISO 8791-2 TAPPI UM-535	ml/min	±50	150	150	150	160	170	200	230	-	-	-	-
Cobb	ISO 535:1991 TAPPI T441	g/m ²	±20	30	30	30	35	40	45	50	50	55	60	60

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature. In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 04/15/2026