

Coral Book Ivory 1.65

Description:

High-bulk uncoated paper 1.65 bulk with high opacity and an off-white shade, aimed at the publishing sector. This is an offset paper made with chemical pulp, designed to deliver excellent performance on press.

Designed for offset printing, guaranteed for digital laser and pre-print laser, and recommended by major digital printing press manufacturers.

Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Digital, Flexo, Laser/Dry toner, Offset, Rotogravure

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Coral Book - Sant Joan les Fonts](#)
- [Paper Profile Coral Book - Zaragoza](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral Book Ivory 1.65

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90
Substance	ISO 536	g/m ²	±4%	70	80	90
Thickness	ISO 534 TAPPI T411	µm	-	115.5	132.0	148.5
Bulk	ISO 534 TAPPI T411	cm ³ /g	±0.03	1.65	1.65	1.65
Opacity	ISO 2471 TAPPI T519	%	-2.0	84.0	86.0	88.0
Color a* D65/10°	ISO 5631-2	abs.	-	-0.05	-0.05	-0.05
Color b* D65/10°	ISO 5631-2	abs.	-	12.3	12.3	12.3
Cobb	ISO 535 TAPPI T441	g/m ²	≤50	35	35	35
Relative humidity	TAPPI T502	%	±7	40	40	40

Storage recommendations

Paper dimensions are very sensible to humidity variations that is why we supply paper in waterproof packaging. Once the packaging is opened, a moisture exchange can take place between the paper and the environment.

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature. In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Before starting a production run, check that the printability is correct on both sides of 30-50 sheets.

Values are subject to change without notice.
Last update: 04/15/2026