

Coral FP

Description:

Uncoated paper for Flexible Packaging applications

End uses:

Flexible packaging

Print methods:

Flexo, Offset

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [EMAS Zaragoza mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral FP

Technical specifications

Property	Test Method	Unit	Tolerance	40	50	60	70
Substance	ISO 536 TAPPI T410	g/m ²	±4%	40	50	60	70
Thickness	ISO 534 TAPPI T411	µm	±4%	51	63	73	85
Cobb	ISO 535 TAPPI T411	g/m ²	±5	25	30	30	30
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	≥ 0.80*STD	2.7	3.8	4.5	5.5
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	≥ 0.80*STD	2.4	3.0	3.2	3.8
Bursting strength	ISO 2758 TAPPI T403	kPa	-40	150	205	230	290
Tear resistance MD/CD	ISO 1974 TAPPI T414	mN	≥0.80*STD	260/280	310/370	410/450	520/520

Values are subject to change without notice.

Last update: 04/15/2026