

KraFit Bag

Description:

Kraft paper made with 100% eucalyptus (unbleached paper)

End uses:

Flexible packaging

Print methods:

Flexo

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile KraFit Bag](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

KraFit Bag

Technical specifications

Property	Test Method	Unit	Tolerance	80	90	100	110
Substance	ISO 536 TAPPI T410	g/m ²	±4%	80	90	100	110
Thickness	ISO 534 TAPPI T411	µm	±4%	98	110	123	136
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1.23	1.22	1.23	1.24
Cobb	ISO 535	g/m ²	±5	30	30	30	30
Tensile strength MD	ISO 1924-2 TAPPI T494	kN/m	-1.0	9.0	9.1	9.6	10.5
Tensile strength CD	ISO 1924-2 TAPPI T494	kN/m	-0.5	4.0	4.1	4.3	4.9
Bursting strength	ISO 2758 TAPPI T403	Kg/cm ²	-0.5	3.6	3.7	3.9	4.1
Tear resistance MD/CD	ISO 1974 TAPPI T414	mN	≥0.80*STD	750/800	840/900	940/1020	1040/1100

Values are subject to change without notice.

Last update: 04/15/2026