

## KraFit FP

### Description:

Kraft paper made with 100% virgin unbleached pulp for Flexible Packaging Applications

### End uses:

Flexible packaging

### Print methods:

Flexo

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## KraFit FP

### Technical specifications

| Property            | Test Method              | Unit             | Tolerance  | 40  | 50  | 60  | 70  |
|---------------------|--------------------------|------------------|------------|-----|-----|-----|-----|
| Substance           | ISO 536<br>TAPPI T410    | g/m <sup>2</sup> | ±4%        | 40  | 50  | 60  | 70  |
| Thickness           | ISO 534<br>TAPPI T411    | µm               | ±4%        | 53  | 63  | 77  | 90  |
| Cobb                | ISO 535<br>TAPPI T411    | g/m <sup>2</sup> | ±5         | 25  | 30  | 30  | 30  |
| Tensile strength MD | ISO 1924-2<br>TAPPI T494 | kN/m             | ≥ 0.80*STD | 3.3 | 4.4 | 5.6 | 7.2 |
| Tensile strength CD | ISO 1924-2<br>TAPPI T494 | kN/m             | ≥ 0.80*STD | 2.5 | 3.5 | 4.7 | 5.2 |
| Bursting strength   | ISO 2758<br>TAPPI T403   | kPa              | -40        | 150 | 210 | 280 | 380 |

Values are subject to change without notice.

Last update: 04/15/2026